

Please type a plus sign (+) inside this box



PTO/SB/05 (4/98)

Approved for use through 09/30/2000. OMB 0651-0032  
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

# UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Attorney Docket No.	033808.136
First Inventor or Application Identifier	C. LACROIX and A. BOUILLOU
Title	THERMOPLASTIC POLYESTER COMPOSITIONS HAVING IMPROVED IMPACT PROPERTIES
Express Mail Label No.	N/A

## APPLICATION ELEMENTS

See MPEP chapter 1500 concerning design patent application contents.

ADDRESS TO

Assistant Commissioner for Patents  
Box Patent Application  
Washington, DC 20231

- 1.  \*Fee Transmittal Form (e.g., PTO/SB/17)  
(Submit an original, and a duplicate for fee processing)
- 2.  Specification [Total Pages 19 ]  
(preferred arrangement set forth below, MPEP 1503.01)
  - Descriptive title of the invention
  - Cross References to Related Applications
  - Statement Regarding Fed sponsored R & D
  - Background of the invention
  - Brief Summary of the invention
  - Brief Description of the Drawings (if filed)
  - Detailed Description
  - Claim(s)
  - Abstract of the Disclosure
- 3.  Drawing(s) (35 U.S.C.113) - FORMAL - [Total Sheets 3 ]
- 4.  Oath or Declaration [Total Pages      ]
  - a.  Newly executed (original or copy)
  - b.  Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 16 completed)
  - i.  DELETION OF INVENTOR(S)  
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 133(b).

- 5.  Microfiche Computer Program (Appendix)
- 6.  Nucleotide and/or Amino Acid Sequence Submission  
(if applicable, all necessary)
  - a.  Computer Readable Copy
  - b.  Paper Copy (identical to computer copy)
  - c.  Statement verifying identity of above copies

## ACCOMPANYING APPLICATIONS PARTS

- 7.  Assignment Papers (cover sheet & document(s))
- 8.  37 C.F.R. § 3.73(b)  
Statement (when there is  Power of Attorney  
an assignee)
- 9.  English Translation Document (if applicable)
- 10.  Information Disclosure Statement (IDS)/PTO-1449  Copies of IDS Citations
- 11.  Preliminary Amendment
- 12.  Return Receipt Postcard (MPEP 503)  
(Should be specifically itemized)
- 13.  \*Small Entity Statement(s) (PTO/SB/09-12)  Statement filed in prior application, Status still proper and desired
- 14.  Certified Copy of Priority Document(s)  
(if foreign priority is claimed)
- 15.  Other: COPY OF FRENCH PARENT APPLICATION (UNCERTIFIED)

\* NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:

Continuation  Divisional  Continuation-in-part (CIP) of prior application No: \_\_\_\_\_ /

Prior application information: Examiner \_\_\_\_\_ Group / Art Unit:

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

## 17. CORRESPONDENCE ADDRESS

Customer Number or Bar Code Label



or  Correspondence address below

(Insert Customer No. or Attach bar code label here)

Name	Frederick F. Calvetti				
	SMITH, GAMBRELL & RUSSELL, LLP				
Address	1850 M Street, N.W., Suite 800				
City	Wasington	State	D.C.	Zip Code	20036
Country	USA	Telephone	202-659-2811	Fax	202-659-1462

Name (Print/Type)	Frederick F. Calvetti	Registration No. (Attorney/Agent)	28,557
Signature		Date	11/24/2000

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231

11/24/00  
jc803 U.S. PTO

11/24/00  
jc841 U.S. PTO

0010426-11000

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

# FEE TRANSMITTAL for FY 2001

Patent fees are subject to annual revision.

Complete if Known

Application Number	To be Assigned
Filing Date	24 November 2000
First Named Inventor	Christophe LACROIX and Alain BOUILLLOUX
Examiner Name	To be Assigned
Group / Art Unit	To be Assigned
Attorney Docket No.	033808.136

TOTAL AMOUNT OF PAYMENT (\$) 710

METHOD OF PAYMENT (check one)		FEE CALCULATION (continued)																																																																																																																																																																																																	
1. <input type="checkbox"/> The Commissioner is hereby authorized to charge indicated fees and credit any over payments to:  Deposit Account Number: 02-4300  Deposit Account Name:  <input checked="" type="checkbox"/> Charge Any Additional Fee Required Under 37 CFR 1.16 and 1.17 <input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27		3. ADDITIONAL FEES																																																																																																																																																																																																	
2. <input checked="" type="checkbox"/> Payment Enclosed: <input checked="" type="checkbox"/> Check <input type="checkbox"/> Credit card <input type="checkbox"/> Money Order <input type="checkbox"/> Other		<table border="1"> <thead> <tr> <th>Large Fee Code</th> <th>Entity Fee (\$)</th> <th>Small Fee Code</th> <th>Entity Fee (\$)</th> <th>Fee Description</th> <th>Fee Paid</th> </tr> </thead> <tbody> <tr><td>105</td><td>130</td><td>205</td><td>65</td><td>Surcharge - late filing fee or oath</td><td></td></tr> <tr><td>127</td><td>50</td><td>227</td><td>25</td><td>Surcharge - late provisional filing fee or cover sheet.</td><td></td></tr> <tr><td>139</td><td>130</td><td>139</td><td>130</td><td>Non-English specification</td><td></td></tr> <tr><td>147</td><td>2,520</td><td>147</td><td>2,520</td><td>For filing a request for reexamination</td><td></td></tr> <tr><td>112</td><td>920*</td><td>112</td><td>920*</td><td>Requesting publication of SIR prior to Examiner action</td><td></td></tr> <tr><td>113</td><td>1,840*</td><td>113</td><td>1,840*</td><td>Requesting publication of SIR after Examiner action</td><td></td></tr> <tr><td>115</td><td>110</td><td>215</td><td>55</td><td>Extension for reply within first month</td><td></td></tr> <tr><td>116</td><td>390</td><td>216</td><td>195</td><td>Extension for reply within second month</td><td></td></tr> <tr><td>117</td><td>890</td><td>217</td><td>445</td><td>Extension for reply within third month</td><td></td></tr> <tr><td>118</td><td>1,390</td><td>218</td><td>695</td><td>Extension for reply within fourth month</td><td></td></tr> <tr><td>128</td><td>1,890</td><td>228</td><td>945</td><td>Extension for reply within fifth month</td><td></td></tr> <tr><td>119</td><td>310</td><td>219</td><td>155</td><td>Notice of Appeal</td><td></td></tr> <tr><td>120</td><td>310</td><td>220</td><td>155</td><td>Filing a brief in support of an appeal</td><td></td></tr> <tr><td>121</td><td>270</td><td>221</td><td>135</td><td>Request for oral hearing</td><td></td></tr> <tr><td>138</td><td>1,510</td><td>138</td><td>1,510</td><td>Petition to institute a public use proceeding</td><td></td></tr> <tr><td>140</td><td>110</td><td>240</td><td>55</td><td>Petition to revive - unavoidable</td><td></td></tr> <tr><td>141</td><td>1,240</td><td>241</td><td>620</td><td>Petition to revive - unintentional</td><td></td></tr> <tr><td>142</td><td>1,240</td><td>242</td><td>620</td><td>Utility issue fee (or reissue)</td><td></td></tr> <tr><td>143</td><td>440</td><td>243</td><td>220</td><td>Design issue fee</td><td></td></tr> <tr><td>144</td><td>600</td><td>244</td><td>300</td><td>Plant issue fee</td><td></td></tr> <tr><td>122</td><td>130</td><td>122</td><td>130</td><td>Petitions to the Commissioner</td><td></td></tr> <tr><td>123</td><td>50</td><td>123</td><td>50</td><td>Petitions related to provisional applications</td><td></td></tr> <tr><td>126</td><td>240</td><td>126</td><td>240</td><td>Submission of Information Disclosure Stmt</td><td></td></tr> <tr><td>581</td><td>40</td><td>581</td><td>40</td><td>Recording each patent assignment per property (times number of properties)</td><td></td></tr> <tr><td>146</td><td>710</td><td>246</td><td>355</td><td>Filing a submission after final rejection (37 CFR § 1.129(a))</td><td></td></tr> <tr><td>149</td><td>710</td><td>249</td><td>355</td><td>For each additional invention to be examined (37 CFR § 1.129(b))</td><td></td></tr> <tr><td>179</td><td>710</td><td>279</td><td>355</td><td>Request for Continued Examination (RCE)</td><td></td></tr> <tr><td>169</td><td>900</td><td>169</td><td>900</td><td>Request for expedited examination of a design application</td><td></td></tr> <tr><td colspan="5">Other fee (specify)</td><td></td></tr> <tr><td colspan="5">*Reduced by Basic Filing Fee Paid</td><td></td></tr> <tr><td colspan="5">SUBTOTAL (3)</td><td>(\$) 0</td></tr> </tbody> </table>		Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description	Fee Paid	105	130	205	65	Surcharge - late filing fee or oath		127	50	227	25	Surcharge - late provisional filing fee or cover sheet.		139	130	139	130	Non-English specification		147	2,520	147	2,520	For filing a request for reexamination		112	920*	112	920*	Requesting publication of SIR prior to Examiner action		113	1,840*	113	1,840*	Requesting publication of SIR after Examiner action		115	110	215	55	Extension for reply within first month		116	390	216	195	Extension for reply within second month		117	890	217	445	Extension for reply within third month		118	1,390	218	695	Extension for reply within fourth month		128	1,890	228	945	Extension for reply within fifth month		119	310	219	155	Notice of Appeal		120	310	220	155	Filing a brief in support of an appeal		121	270	221	135	Request for oral hearing		138	1,510	138	1,510	Petition to institute a public use proceeding		140	110	240	55	Petition to revive - unavoidable		141	1,240	241	620	Petition to revive - unintentional		142	1,240	242	620	Utility issue fee (or reissue)		143	440	243	220	Design issue fee		144	600	244	300	Plant issue fee		122	130	122	130	Petitions to the Commissioner		123	50	123	50	Petitions related to provisional applications		126	240	126	240	Submission of Information Disclosure Stmt		581	40	581	40	Recording each patent assignment per property (times number of properties)		146	710	246	355	Filing a submission after final rejection (37 CFR § 1.129(a))		149	710	249	355	For each additional invention to be examined (37 CFR § 1.129(b))		179	710	279	355	Request for Continued Examination (RCE)		169	900	169	900	Request for expedited examination of a design application		Other fee (specify)						*Reduced by Basic Filing Fee Paid						SUBTOTAL (3)					(\$) 0
Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description	Fee Paid																																																																																																																																																																																														
105	130	205	65	Surcharge - late filing fee or oath																																																																																																																																																																																															
127	50	227	25	Surcharge - late provisional filing fee or cover sheet.																																																																																																																																																																																															
139	130	139	130	Non-English specification																																																																																																																																																																																															
147	2,520	147	2,520	For filing a request for reexamination																																																																																																																																																																																															
112	920*	112	920*	Requesting publication of SIR prior to Examiner action																																																																																																																																																																																															
113	1,840*	113	1,840*	Requesting publication of SIR after Examiner action																																																																																																																																																																																															
115	110	215	55	Extension for reply within first month																																																																																																																																																																																															
116	390	216	195	Extension for reply within second month																																																																																																																																																																																															
117	890	217	445	Extension for reply within third month																																																																																																																																																																																															
118	1,390	218	695	Extension for reply within fourth month																																																																																																																																																																																															
128	1,890	228	945	Extension for reply within fifth month																																																																																																																																																																																															
119	310	219	155	Notice of Appeal																																																																																																																																																																																															
120	310	220	155	Filing a brief in support of an appeal																																																																																																																																																																																															
121	270	221	135	Request for oral hearing																																																																																																																																																																																															
138	1,510	138	1,510	Petition to institute a public use proceeding																																																																																																																																																																																															
140	110	240	55	Petition to revive - unavoidable																																																																																																																																																																																															
141	1,240	241	620	Petition to revive - unintentional																																																																																																																																																																																															
142	1,240	242	620	Utility issue fee (or reissue)																																																																																																																																																																																															
143	440	243	220	Design issue fee																																																																																																																																																																																															
144	600	244	300	Plant issue fee																																																																																																																																																																																															
122	130	122	130	Petitions to the Commissioner																																																																																																																																																																																															
123	50	123	50	Petitions related to provisional applications																																																																																																																																																																																															
126	240	126	240	Submission of Information Disclosure Stmt																																																																																																																																																																																															
581	40	581	40	Recording each patent assignment per property (times number of properties)																																																																																																																																																																																															
146	710	246	355	Filing a submission after final rejection (37 CFR § 1.129(a))																																																																																																																																																																																															
149	710	249	355	For each additional invention to be examined (37 CFR § 1.129(b))																																																																																																																																																																																															
179	710	279	355	Request for Continued Examination (RCE)																																																																																																																																																																																															
169	900	169	900	Request for expedited examination of a design application																																																																																																																																																																																															
Other fee (specify)																																																																																																																																																																																																			
*Reduced by Basic Filing Fee Paid																																																																																																																																																																																																			
SUBTOTAL (3)					(\$) 0																																																																																																																																																																																														
1. BASIC FILING FEE																																																																																																																																																																																																			
Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description	Fee Paid																																																																																																																																																																																														
101	710	201	355	Utility filing fee	710.00																																																																																																																																																																																														
106	320	206	160	Design filing fee																																																																																																																																																																																															
107	490	207	245	Plant filing fee																																																																																																																																																																																															
108	710	208	355	Reissue filing fee																																																																																																																																																																																															
114	150	214	75	Provisional filing fee																																																																																																																																																																																															
SUBTOTAL (1)					(\$) 710																																																																																																																																																																																														
2. EXTRA CLAIM FEES																																																																																																																																																																																																			
Total Claims	10	-20**	= 0	Extra Claims	Fee from below	Fee Paid																																																																																																																																																																																													
Independent Claims	2	-3**	= 0																																																																																																																																																																																																
Multiple Dependent	0																																																																																																																																																																																																		
Large Fee Code	Entity Fee (\$)	Small Fee Code	Entity Fee (\$)	Fee Description																																																																																																																																																																																															
103	18	203	9	Claims in excess of 20																																																																																																																																																																																															
102	80	202	40	Independent claims in excess of 3																																																																																																																																																																																															
104	270	204	135	Multiple dependent claim, if not paid																																																																																																																																																																																															
109	80	209	40	** Reissue independent claims over original patent																																																																																																																																																																																															
110	18	210	9	** Reissue claims in excess of 20 and over original patent																																																																																																																																																																																															
SUBTOTAL (2)					(\$) 0																																																																																																																																																																																														

\*\*or number previously paid, if greater; For Reissues, see above

SUBMITTED BY		Complete (if applicable)			
Name (Print/Type)	Frederick F. Calvetti	Registration No. Attorney/Agent	28,557	Telephone	202-659-2811
Signature		Date	24 November 2000		

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2036.

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

Applicant: Christophe LACROIX and Alain BOUILLOUX

Serial No.: Unassigned

Examiner: Unassigned

Filed: Concurrently Herewith

Group Art Unit: Unassigned

For: THERMOPLASTIC POLYESTER COMPOSITIONS  
HAVING IMPROVED IMPACT PROPERTIES

**PRELIMINARY AMENDMENT**

Honorable Commissioner for Patents  
Washington, D.C. 20231

Sir:

Prior to calculating the filing fee for the above-identified new U.S. patent application, kindly amend the application as follows.

**IN THE SPECIFICATION:**

Please amend the specification as follows.

Page 1, line 5, delete “[Field of the invention]” and insert --FIELD OF THE INVENTION--; and

line 25, delete “[Prior art]” and insert --BACKGROUND OF THE INVENTION--.

Page 3, after “EP 531,008 TABLE”, delete “[The technical problem]” and insert the following:

**--BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1 is a diagram illustrating the Charpy Impact vs AX/Core Shell ratio at -40°C;

Figure 2 is a diagram illustrating the Charpy Impact vs AX/Core Shell ratio at +23°C; and

Figure 3 is a diagram illustrating the MFI vs AX/Core Shell ratio at 250°C.--.

033808.136



## THERMOPLASTIC POLYESTER COMPOSITIONS HAVING IMPROVED IMPACT PROPERTIES

---

5 [Field of the invention]

The present invention relates to thermoplastic polyesters having improved impact properties and to impact-modifier compositions.

Thermoplastic polyesters, such as PBT (polybutylene terephthalate)  
10 and PET (polyethylene terephthalate) possess excellent dimensional-stability, heat-resistance and chemical-resistance properties and are used in the electrical, electronic and motor-vehicle fields. However, at high temperature, during conversion operations, a reduction in the molecular weight of the polymer may occur, leading to a reduction in the impact  
15 properties. In addition, polyesters have poor fracture-resistance properties in the case of notched components.

The present invention provides thermoplastic polymers in which an impact-modifier composition is added in order to obtain improved impact properties, especially low-temperature toughness. The present invention  
20 also relates to this impact-modifier composition that is added to the polyesters to improve the impact properties thereof. These modifier compositions make it possible to achieve impact properties superior to those obtained with each of the compounds separately.

25 [Prior art]

Patent US 4,753,890 (= EP 174,343) describes polyesters, such as, for example, polyethylene terephthalate (PET) or polybutylene terephthalate (PBT), which are modified by ethylene-alkyl (meth)acrylate-glycidyl  
30 (meth)acrylate copolymers.

Patent US 5,369,154 describes PET/polycarbonate blends containing four different modifiers: a copolymer comprising an epoxide, a copolymer of the core-shell type, an SBR- or SBS- or EPR-type elastomer and a copolymer

of the SAN or ABS type. These core-shell copolymers comprise fine particles having an elastomer core and a thermoplastic shell.

Patent EP 115,015 describes PET or PBT containing linear low-density polyethylene (LLDPE), glass fibres and optionally a core-shell  
5 copolymer.

Patent EP 133,993 describes PET containing a core-shell copolymer and a copolymer of ethylene with either an alkyl acrylate or (meth)acrylic acid.

Japanese Patent Application JP 01,247,454 A, published on  
10 3 October 1989 describes PBT containing an ethylene-alkyl (meth)acrylate copolymer and an ethylene-glycidyl methacrylate copolymer.

Patents EP 838,501 and EP 511,475 describe compositions similar to those of the above Japanese application.

Patent EP 803,537 describes PET and polycarbonate containing a  
15 copolymer comprising glycidyl methacrylate. Firstly, the polycarbonate and the copolymer comprising glycidyl methacrylate are blended together and then this blend is incorporated into the PET.

Patent EP 187,650 describes PET containing a core-shell copolymer and a copolymer of ethylene with either maleic anhydride or a (meth)acrylic  
20 acid.

Patent EP 737,715 describes PBTs modified by an impact modifier consisting of an ethylene-methyl methacrylate-glycidyl methacrylate copolymer/core-shell copolymer blend. The amount of impact modifier is from 5 to 20 parts per 100 parts of polyester, i.e. 4.8 to 16.7% for 95.2 to  
25 83.7% of polyester, respectively. The proportions of the glycidyl methacrylate copolymer to the core-shell copolymer are in the ratio 15/85 to 20/80. In the examples, the amount of impact modifier is from 18 parts per 100 parts of polyester, i.e. 15.3%, and the proportion of glycidyl methacrylate copolymer to the core-shell copolymer is in the ratio 3/15, i.e.  
30 17/83.

Patent EP 531,008 describes spent (recycled) PBT/polycarbonate (PC) blends containing core-shell copolymers, to which functionalized copolymers are added in order to make them into a new thermoplastic.



functional groups capable of reacting with the functional groups of the polyesters. This reactivity makes it possible to ensure a fine and homogeneous dispersion of the modifier as well as good adhesion. The core-shell copolymer may itself also be functionalized in order to allow  
5 better adhesion to the matrix. However, this reactivity is sometimes high and may lead to a reduction in the melt flow index. This reduction in the melt flow index is prejudicial to the injection moulding of large parts or of fine parts.

It has now been found that it is possible to improve the impact  
10 properties of thermoplastic polyesters containing essentially no polycarbonate by adding to them two kinds of modifier, namely (a) a core-shell copolymer and (b) either an ethylene-unsaturated epoxide copolymer or an ethylene-carboxylic acid anhydride copolymer or a blend of them but in proportions in the polyester and in (b)/(a) ratios different from those of  
15 the prior art EP 737,715. Better impact strength is obtained while maintaining and even improving the melt flow index. It has also been discovered that the impact strength can be improved even more by adding polycarbonate to thermoplastic polyesters containing (a) and (b) in proportions (b)/(a) different from those of the prior art EP 531,008 and lying  
20 between 90/10 and 70/30.

[Brief description of the invention]

The present invention relates to thermoplastic polyester  
25 compositions not comprising polycarbonate, which comprise, by weight:

- (i) a thermoplastic polyester;
- (ii) an impact modifier comprising:
  - (a) a core-shell copolymer (A),
  - (b) an ethylene copolymer (B) chosen from ethylene-unsaturated  
30 carboxylic acid anhydride copolymers (B1), ethylene-unsaturated epoxide copolymers (B2) and blends thereof;
- (iii) the (B)/(A) ratio being between 90/10 and 25/75 for proportions of impact modifier between 2 and 40% in 98 to 60% of polyester, respectively,



and advantageously between 5 and 40% in 95 to 60% of polyester, respectively;

(iv) the (B)/(A) ratio being between 25/75 and 10/90 for proportions of impact modifier between 18 and 40% in 82 to 60% of polyester, respectively.

The present invention also relates to thermoplastic polyester compositions comprising, by weight, the total being 100%:

(i) 98 to 60%, preferably 95 to 60%, of a thermoplastic polyester;

(ii) 2 to 40%, preferably 5 to 40%, of an impact modifier comprising:

(a) a core-shell copolymer (A),

(b) an ethylene copolymer (B) chosen from ethylene-unsaturated carboxylic acid anhydride copolymers (B1), ethylene-unsaturated epoxide copolymers (B2) and blends thereof;

(iii) the (B)/(A) ratio being between 90/10 and 70/30;

(iv) these compositions comprising up to 30 parts of polycarbonate per 100 parts of polyester.

The present invention also relates to an impact-modifier composition which can be added to the thermoplastic polyesters to improve their impact properties and which comprise:

(a) a core-shell copolymer (A);

(b) an ethylene copolymer (B) chosen from ethylene-unsaturated carboxylic acid anhydride copolymers (B1), ethylene-unsaturated epoxide copolymers (B2) and blends thereof;

- the (B)/(A) ratio being between 90/10 and 25/75 for proportions of impact modifier between 2 and 40% in 98 to 60% of polyester, respectively, and advantageously between 5 and 40% in 95 to 60% of polyester, respectively;

- the (B)/(A) ratio being between 25/75 and 10/90 for proportions of impact modifier between 18 and 40% in 82 to 60% of polyester, respectively.

[Detailed description of the invention]

The term "thermoplastic polyester" denotes polymers which are saturated products coming from the condensation of glycols and of dicarboxylic acids, or of their derivatives. Preferably, they comprise the products of the condensation of aromatic dicarboxylic acids having from 8 to 14 carbon atoms and of at least one glycol chosen from the group consisting of neopentyl glycol, cyclohexanedimethanol and aliphatic glycols of formula  $\text{HO}(\text{CH}_2)_n\text{OH}$  in which  $n$  is an integer ranging from 2 to 10. Up to 50 mol% of the aromatic dicarboxylic acid may be replaced with at least one other aromatic dicarboxylic acid having from 8 to 14 carbon atoms, and/or up to 20 mol% may be replaced with an aliphatic dicarboxylic acid having from 2 to 12 carbon atoms.

The preferred polyesters are polyethylene terephthalate (PET), poly(1,4-butylene) terephthalate (PBT), 1,4-cyclohexylene dimethylene terephthalate/isophthalate) and other esters derived from aromatic dicarboxylic acids such as isophthalic acid, dibenzoic acid, naphthalene dicarboxylic acid, 4,4'-diphenylenedicarboxylic acid, bis(p-carboxyphenyl)methane acid, ethylene bis(p-benzoic) acid, 1,4-tetramethylene bis(p-oxybenzoic) acid, ethylene bis(para-oxybenzoic) acid, 1,3-trimethylene bis(p-oxybenzoic) acid, and glycols such as ethylene glycol, 1,3-trimethylene glycol, 1,4-tetramethylene glycol, 1,6-hexamethylene glycol, 1,3-propylene glycol, 1,8-octamethylene glycol and 1,10-decamethylene glycol. The MFI of these polyesters, measured at 250°C and with 2.16 kg, may vary from 2 to 100 and advantageously from 10 to 80. "MFI" denotes the melt flow index.

It would not be outside the scope of the invention if the polyesters consisted of several diacids and/or several diols. It is also possible to use a blend of various polyesters.

It would not be outside the scope of the invention if the polyesters contained copolyetheresters. These copolyetheresters are copolymers containing polyester blocks and polyether blocks having polyether units derived from polyetherdiols such as polyethylene glycol (PEG), polypropylene glycol (PPG) or polytetramethylene glycol (PTMG),

dicarboxylic acid units such as terephthalic acid units, and short, chain-extender, diol units such as glycol (ethanediol) or 1,4-butanediol. The linking of the polyethers with the diacids forms the flexible segments whereas the linking of the glycol or butanediol with the diacids forms the rigid segments of the copolyetherester. These copolyetheresters are thermoplastic elastomers. The proportion of these copolyetheresters may represent up to 30 parts per 100 parts of thermoplastic polyester.

**With regard to the core-shell copolymer (A)**, this is in the form of fine particles having an elastomer core and at least one thermoplastic shell, the particle size being generally less than 1  $\mu\text{m}$  and advantageously between 200 and 500 nm. By way of example of the core, mention may be made of isoprene homopolymers or butadiene homopolymers, copolymers of isoprene with at most 30 mol% of a vinyl monomer and copolymers of butadiene with at most 30 mol% of a vinyl monomer. The vinyl monomer may be styrene, an alkylstyrene, acrylonitrile or an alkyl (meth)acrylate. Another core family consists of the homopolymers of an alkyl (meth)acrylate and the copolymers of an alkyl (meth)acrylate with at most 30 mol% of a vinyl monomer. The alkyl (meth)acrylate is advantageously butyl acrylate. The vinyl monomer may be styrene, an alkylstyrene, acrylonitrile, butadiene or isoprene. The core of the copolymer (A) may be completely or partly crosslinked. All that is required is to add at least difunctional monomers during the preparation of the core; these monomers may be chosen from poly(meth)acrylic esters of polyols, such as butylene di(meth)acrylate and trimethylolpropane trimethacrylate. Other difunctional monomers are, for example, divinylbenzene, trivinylbenzene, vinyl acrylate and vinyl methacrylate. The core can also be crosslinked by introducing into it, by grafting or as a comonomer during the polymerization, unsaturated functional monomers such as anhydrides of unsaturated carboxylic acids, unsaturated carboxylic acids and unsaturated epoxides. Mention may be made, by way of example, of maleic anhydride, (meth)acrylic acid and glycidyl methacrylate.

The shell(s) are styrene homopolymers, alkylstyrene homopolymers or methyl methacrylate homopolymers, or copolymers comprising at least

70 mol% of one of the above monomers and at least one comonomer chosen from the other above monomers, vinyl acetate and acrylonitrile. The shell may be functionalized by introducing into it, by grafting or as a comonomer during the polymerization, unsaturated functional monomers such as anhydrides of unsaturated carboxylic acids, unsaturated carboxylic acids and unsaturated epoxides. Mention may be made, for example, of maleic anhydride, (meth)acrylic acid and glycidyl methacrylate. By way of example, mention may be made of core-shell copolymers (A) having a polystyrene shell and core-shell copolymers (A) having a PMMA shell. There are also core-shell copolymers (A) having two shells, one made of polystyrene and the other, on the outside, made of PMMA. Examples of copolymers (A) and their method of preparation are described in the following patents: US 4,180,494, US 3,808,180, US 4,096,202, US 4,260,693, US 3,287,443, US 3,657,391, US 4,299,928 and US 3,985,704.

Advantageously, the core represents, by weight, 70 to 90% of (A) and the shell represents 30 to 10%.

By way of example of a copolymer (A), mention may be made of that consisting (i) of 75 to 80 parts of a core comprising at least 93 mol% of butadiene, 5 mol% of styrene and 0.5 to 1 mol% of divinylbenzene and (ii) of 25 to 20 parts of two shells essentially of the same weight, the inner one made of polystyrene and the outer one made of PMMA.

**With regard to ethylene-unsaturated carboxylic acid anhydride copolymers (B1)**, these may be polyethylenes grafted by an unsaturated carboxylic acid anhydride or ethylene-unsaturated carboxylic acid anhydride copolymers which are obtained, for example, by radical polymerization.

The unsaturated carboxylic acid anhydride may be chosen, for example, from maleic, itaconic, citraconic, allylsuccinic, cyclohex-4-ene-1,2-dicarboxylic, 4—methylenecyclohex-4-ene-1,2-dicarboxylic, bicyclo-[2.2.1]hept-5-ene-2,3-dicarboxylic and x—methylbicyclo[2.2.1]hept-5-ene-2,2-dicarboxylic anhydrides. Advantageously, maleic anhydride is used. It would not be outside the scope of the invention to replace all or part of the

anhydride with an unsaturated carboxylic acid such as, for example, (meth)acrylic acid.

With regard to the polyethylenes onto which the unsaturated carboxylic acid anhydride is grafted, the term "polyethylene" should be understood to mean homopolymers or copolymers.

By way of comonomers, mention may be made of:

- alpha-olefins, advantageously those having from 3 to 30 carbon atoms; by way of examples of alpha-olefins, mention may be made of propylene, 1-butene, 1-pentene, 3-methyl-1-butene, 1-hexene, 4-methyl-1-pentene, 3-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1—eicocene, 1-dococene, 1-tetracocene, 1-hexacocene, 1—octacocene and 1-triacontene; these alpha-olefins may be used separately or as a mixture of two or more of them;
- esters of unsaturated carboxylic acids, such as, for example, alkyl (meth)acrylates, the alkyls possibly having up to 24 carbon atoms; examples of alkyl acrylates or methacrylates are especially methyl methacrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate and 2-ethylhexyl acrylate;
- vinyl esters of saturated carboxylic acids, such as, for example, vinyl acetate or vinyl propionate;
- dienes such as, for example, 1,4-hexadiene.

The polyethylene may include several of the above comonomers.

Advantageously, the polyethylene, which may be a blend of several polymers, comprises at least 50 mol% and preferably 75 mol% of ethylene and its density may be between 0.86 and 0.98 g/cm<sup>3</sup>. The MFI (Melt Flow Index at 190°C/2.16 kg) is advantageously between 0.1 and 1000 g/10 min.

By way of example of polyethylenes, mention may be made of:

- low-density polyethylene (LDPE)
- high-density polyethylene (HDPE)
- linear low-density polyethylene (LLDPE)
- very low-density polyethylene (VLDPE)

- polyethylene obtained by metallocene catalysis, that is to say polymers obtained by the copolymerization of ethylene and of an alpha-olefin such as propylene, butene, hexene or octene in the presence of a single-site catalyst generally consisting of a zirconium or titanium atom and of two alkyl cyclic molecules linked to the metal. More specifically, the metallocene catalysts are usually composed of two cyclopentadiene rings linked to the metal. These catalysts are frequently used with aluminoxanes as cocatalysts or activators, preferably methylaluminoxane (MAO). Hafnium may also be used as the metal to which the cyclopentadiene is fixed. Other metallocenes may include transition metals of Groups IV A, V A and VI A. Metals from the series of lanthanides may also be used.

- EPR (ethylene-propylene-rubber) elastomers;
- EPDM (ethylene-propylene-diene) elastomers;
- blends of polyethylene with an EPR or an EPDM;
- ethylene-alkyl (meth)acrylate copolymers possibly containing up to 60%, and preferably 2 to 40%, by weight of (meth)acrylate.

The grafting is an operation known per se.

With regard to the ethylene-unsaturated carboxylic acid anhydride copolymers, that is to say those in which the unsaturated carboxylic acid anhydride is not grafted, these are copolymers of ethylene, the unsaturated carboxylic acid anhydride and, optionally another monomer which may be chosen from the comonomers that were mentioned above in the case of the ethylene copolymers intended to be grafted.

Advantageously, ethylene-maleic anhydride copolymers and ethylene-alkyl (meth)acrylate-maleic anhydride copolymers are used. These copolymers comprise from 0.2 to 10% by weight of maleic anhydride and from 0 to 40%, preferably 5 to 40%, by weight of alkyl (meth)acrylate. Their MFIs are between 0.5 and 200 (190°C/2.16 kg). The alkyl (meth)acrylates have already been described above. It is possible to use a blend of several copolymers (B1), and it is also possible to use an ethylene-maleic anhydride copolymer/ethylene-alkyl (meth)acrylate-maleic anhydride copolymer blend.

The copolymer (B1) is commercially available, produced by radical polymerization at a pressure which may range between 200 and 2500 bar and is sold in the form of granules.

**With regard to the ethylene-unsaturated epoxide copolymers (B2)**, these may be obtained by the copolymerization of ethylene with an unsaturated epoxide or by grafting the unsaturated epoxide to the polyethylene. The grafting may be carried out in the solvent phase or onto the polyethylene in the melt in the presence of a peroxide. These grafting techniques are known per se. With regard to the copolymerization of ethylene with an unsaturated epoxide, it is possible to use so-called radical polymerization processes usually operating at pressures between 200 et 2500 bar.

By way of example of unsaturated epoxides, mention may be made of:

- aliphatic glycidyl esters and ethers, such as allyl glycidyl ether, vinyl glycidyl ether, glycidyl maleate, glycidyl itaconate, glycidyl acrylate and glycidyl methacrylate; and
- alicyclic glycidyl esters and ethers, such as 2-cyclohex-1-ene glycidyl ether, diglycidyl cyclohexene-4-5-dicarboxylate, glycidyl cyclohexene-4-carboxylate, glycidyl 2-methyl-5-norbornene-2-carboxylate and diglycidyl *endo-cis*-bicyclo[2.2.1]hept-5-ene-2,3-dicarboxylate.

With regard to grafting, the copolymer is obtained by grafting an ethylene homopolymer or copolymer as described in the case of (B1), except that an epoxide is grafted instead of an anhydride. With regard to copolymerization, this is also similar to (B1) except that an epoxide is used; it may also have other comonomers, as in the case of (B1).

The product (B2) is advantageously an ethylene-alkyl (meth)acrylate-unsaturated epoxide copolymer or an ethylene-unsaturated epoxide copolymer. Advantageously, it may contain up to 40%, preferably 5 to 40%, by weight of alkyl (meth)acrylate and up to 10%, preferably 0.1 to 8%, by weight of unsaturated epoxide.


Advantageously, the epoxide is glycidyl (meth)acrylate.

Advantageously, the alkyl (meth)acrylate is chosen from methyl (meth)acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate and

2-ethylhexyl acrylate. The amount of alkyl (meth)acrylate is advantageously from 20 to 35%. The MFI is advantageously between 0.5 and 200 (in g/10 min. at 190°C/2.16 kg). It is possible to use a blend of several copolymers (B2), and it is also possible to use an ethylene-alkyl  
 5 (meth)acrylate-unsaturated epoxide copolymer/ethylene-unsaturated epoxide copolymer blend. This copolymer (B2) may be obtained by the radical polymerization of the monomers. It is also possible to use a blend of copolymers (B1) and (B2).


Among the copolymers (B), it is advantageous to use the  
 10 copolymers (B2).

According to another embodiment of the invention, the compositions in which the proportions of (A) and (B) are such that (B)/(A) is between 90/10 and 70/30 may contain polycarbonate. The impact strength is thus improved. In general, the term "polycarbonate" denotes polymers  
 15 comprising the following units:



in which R<sub>1</sub> is an aliphatic, alicyclic or aromatic divalent group; the aliphatic  
 20 and alicyclic groups may contain up to 8 carbon atoms. By way of example of R<sub>1</sub>, mention may be made of ethylene, propylene, trimethylene, tetramethylene, hexamethylene, dodecamethylene, poly(1,4-[2-butenylene]), poly(1,10-[(2-ethyldecylene)]), 1,3-cyclopentylene, 1,3-cyclohexylene, 1,4-cyclohexylene, m-phenylene, p-phenylene,  
 25 4,4'-diphenylene, 2,2-bis(4-phenylene)propane and benzene-1,4-dimethylene. Advantageously, at least 60% of the R<sub>1</sub> groups in the polycarbonate and preferably all the groups R<sub>1</sub> are aromatic groups of formula:

30





in which  $R_2$  et  $R_3$  are divalent monocyclic aromatic radicals and Y is a linking radical in which one or two atoms separate  $R_2$  and  $R_3$ . The free valences are generally in the meta or para position with respect to Y.  $R_2$  and  $R_3$  may be substituted or unsubstituted phenylenes; as substituents, mention may be made of alkyl, alkenyl, halogen, nitro and alkoxy. Preferably, the phenylenes are unsubstituted; they may be together or separately meta or para and are preferably para. The linking radical Y is preferably such that one atom separates  $R_2$  from  $R_3$  and is preferably a hydrocarbon radical such as methylene, cyclohexylmethylene, 2-[2.2.1]bicycloheptylmethylene, ethylene, 2,2-propylene, 1,1-(2,2-dimethylpropylene), 1,1-cyclohexylene, 1,1-cyclopentadecylene, cyclododecylene, carbonyl, the oxy radical, the thio radical and sulfone. Preferably,  $R_1$  is 2,2-bis(4-phenylene)propane which comes from bisphenol A, that is to say Y is isopropylidene and  $R_2$  and  $R_3$  are each p-phenylene. Advantageously, the intrinsic viscosity of the polycarbonate, measured in methylene chloride at 25°C, is between 0.3 and 1 dl/g.

The proportion of polycarbonate may represent up to 30 parts per 100 parts of thermoplastic polyester and advantageously from 2 to 20 parts.

Advantageously, the thermoplastic polyester compositions of the invention comprise, per 100 parts by weight, 75 to 95 parts of polyester for 25 to 5 parts of impact modifier, respectively.

The invention also relates to an impact-modifier composition comprising (A) and (B) which can be added to the thermoplastic polyesters to improve their impact properties. In this impact-modifier composition, the proportions of (A) and (B) were defined above.

The thermoplastic polyesters of the invention may also include, in addition to the impact modifier, slip agents, antiblocking agents, antioxidants, UV stabilizers and fillers. The fillers may be glass fibres, fire retardants, talc or chalk.

The thermoplastic polyester/impact-modifier blends are prepared by the usual techniques for thermoplastic polymers in single-screw or twin-



All the examples were produced with compositions comprising 80% by weight of PBT and 20% by weight of impact modifier. The notched Charpy impact strength complies with the ISO 179:93 standard; the higher the value the better the impact strength.

5

**FIGURE 1** shows the notched Charpy impact strength at  $-40^{\circ}\text{C}$  for PBT containing impact modifier consisting either of AX or of core-shell copolymer or of their blends. Two kinds of AX: AX 8900 and AX 8930 and two kinds of core-shell copolymer: EXL 2314 and E920 were used.

**FIGURE 2** shows the impact strengths of these same compositions at  $+23^{\circ}\text{C}$ . In these figures and in the tables, the epoxide copolymer has been denoted by AX and the core-shell copolymer by CS. The AX/CS ratio is the weight ratio, "30/70" meaning 30 parts of AX to 70 parts of CS. The values are also given in **TABLE 1** and **TABLE 2**.

15

**TABLE 1**

PBT+20%(AX+CS) AX=AX 8900 or AX 8930 CS=EXL 2314 or E920	Notched Charpy impact strength at $-40^{\circ}\text{C}$			
	AX 8900 EXL 2314	AX 8900/E920	AX 8930 EXL 2314	AX 8930/E920
100/0 AX/CS (comparative)	6.2	6.2	5	5
70/30 AX/CS	9.8	10	8.8	9.9
30/70 AX/CS	7.8	14.75	7.1	9.8
20/80 AX/CS	9.2	10.25		
10/90 AX/CS		13.8		
0/100 AX/CS (comparative)	6.75	8.2	6.75	8.2

**TABLE 2**

PBT+20%(AX+CS) AX=AX 8900 or AX 8930 CS=EXL 2314 or E920	Notched Charpy impact strength at $+23^{\circ}\text{C}$			
	AX 8900 EXL 2314	AX 8900/E920	AX 8930 EXL 2314	AX 8930/E920
100/0 AX/CS (comparative)	76.4	76.4	55.2	55.2
70/30 AX/CS	99	62.2	67.5	61
30/70 AX/CS	91.8	88.9	82.6	88.4
20/80 AX/CS	87.6	79.5		
10/90 AX/CS		80		



anhydride and from 0 to 40%, preferably 5 to 40%, by weight of alkyl (meth)acrylate.

6 Compositions according to any one of Claims 1 to 4, in which  
5 the ethylene-unsaturated epoxide copolymers (B2) are ethylene-alkyl (meth)acrylate-unsaturated epoxide copolymers obtained by copolymerization of the monomers and contain from 0 to 40% by weight of alkyl (meth)acrylate and up to 10% by weight of unsaturated epoxide.

10 7 Compositions according to any one of the preceding claims, in which the proportions of (A) and (B) are such that the (B)/(A) ratio is between 90/10 and 70/30 and comprising up to 30 parts of polycarbonate per 100 parts of polyester.

15 8 Compositions according to any one of the preceding claims, comprising, per 100 parts by weight, 75 to 95 parts of polyester for 25 to 5 parts of impact modifier, respectively.

20 9 Impact-modifier compositions comprising:  
(a) a shell-core copolymer (A);  
(b) an ethylene copolymer (B) chosen from ethylene-unsaturated carboxylic acid anhydride copolymers (B1), ethylene-unsaturated epoxide copolymers (B2) and blends thereof;  
• the (B)/(A) ratio being between 90/10 and 25/75 for proportions of  
25 impact modifier between 2 and 40% in 98 to 60% of polyester, respectively, and advantageously between 5 and 40% in 95 to 60% of polyester, respectively;  
• the (B)/(A) ratio being between 25/75 and 10/90 for proportions of  
30 impact modifier between 18 and 40% in 82 to 60% of polyester, respectively.

## ABSTRACT

□□□□

### THERMOPLASTIC POLYESTER COMPOSITIONS HAVING IMPROVED IMPACT PROPERTIES

□□□□

**Company named:** ELF ATOCHEM S.A.  
4 & 8 Cours Michelet  
La Défense 10  
92800 PUTEAUX - Hauts-de-Seine

□□□□

**Agent:** Henry NÉEL

□□□□

**Inventors:** Mr Christophe LACROIX  
Mr Alain BOUILLOUX

□□□□

The present invention relates to thermoplastic polyesters, which comprise, by weight:

- (i) a thermoplastic polyester;
- (ii) an impact modifier comprising:
  - (a) a core-shell copolymer (A);
  - (b) an ethylene copolymer (B) chosen from ethylene-unsaturated carboxylic acid anhydride copolymers (B1), ethylene-unsaturated epoxide copolymers (B2) and blends thereof;
- (iii) the (B)/(A) ratio being between 90/10 and 25/75 for proportions of impact modifier between 2 and 40% in 98 to 60% of polyester, respectively;
- (iv) the (B)/(A) ratio being between 25/75 and 10/90 for proportions of impact modifier between 18 and 40% in 82 to 60% of polyester, respectively.

It is particularly useful for PET and PBT.

0004949 112400

FIGURE 1

PBT + 20% ( AX/Core Shell). Charpy Impact vs AX/Core Shell ratio




FIGURE 2

PBT + 20% ( AX/Core Shell). Charpy Impact vs AX/Core Shell ratio






FIGURE 3

PBT + 20% ( AX/Core Shell) : MFI vs AX/Core Shell ratio

